

TECHNICAL DATA SHEET

Torgue PR22 GFR25 BK01 HS01

PA66 %25 GLASS FIBER BLACK HEAT STAB

injection moulding grade, cylindrical granuls

Properties	Test method	Unit	Condition	Values
ISO Shortname	ISO 16396	-	-	PA66-GF25
Density	ISO 1183	g/cm ³		1,28
Viscosity Number (VN)	ISO 307	ml/gr	%0,5(m/v) in %96 (m/m) H ₂ SO ₄	-
Ash Content	ISO 3451	%	750°C 30 min	25
Water absorption	ISO 62	%	saturation in water 23 °C	2,8
Water absorption,(Equilibrium value)	ISO 62	%	50% RH, 23 °C	1,6
Mechanical properties				
Tensile Modulus	ISO 527-2	MPa	23°C	6.250
Young Modulus	ISO 527-2	MPa	23°C	7.000
Tensile Strenght at Break	ISO 527-2	MPa	23°C	120
Tensile Strenght at Yield	ISO 527-2	Mpa	23°C	100
Elongation at Break	ISO 527-2	%	23°C	3,5
Elongation at Yield	ISO 527-2	%	23°C	1,5
Flexural modulus	ISO 178-A	Mpa	23°C	7.000
Flexural Strength	ISO 178-A	Mpa	23°C	140
Charpy notched impact strenght	ISO 179-1eA	kJ/m ²	23°C	8,0
Charpy notched impact strenght	ISO 179-1eA	kJ/m ²	-30°C	7,5
Charpy unnotched impact strenght	ISO 179-1eU	kJ/m ²	23°C	-
Charpy unnotched impact strenght	ISO 179-1eU	kJ/m ²	-30°C	-
Izod notched impact impact strenght	ISO 180/1A	kJ/m ²	23°C	7,3
Izod notched impact impact strenght	ISO 180/1A	kJ/m ²	-30°C	6,7

Thermal Properties				
Vicat softening temperature	ISO 306	°C	50 N - 50 °C/h	-
Deflection temperature 1.8 MPa (HDT A)	ISO 75-1-12	°C	1,80 Mpa	230
Deflection temperature 0.45 MPa (HDT B)	ISO 75-1-12	°C	0,45 Mpa	240
Flammability				
Flame Rating	UL94	class	1,6 mm	HB
GWFI (<i>Glow Wire Flammability Index</i>)	IEC 60695	°C	2 mm	600
GWIT (<i>Glow Wire Ignitability Index</i>)	IEC 60695	°C	2 mm	600
Electrical properties				
Comparative tracking index, CTI	IEC 60112	V	3 mm-Solution A	500
Volume resistivity	IEC 60093	ohm*m	dry	1E+13
Surface resistivity	IEC 60093	ohm	dry	1E+14
Processing				
Melting Temperature, DSC	ISO 11357-1/-3	°C	-	260
MVR(Melt Volume Rate)	ISO 1133	cm ³ /10 min	280 °C/ 5 kg	-
Drying temperature dry air dryer	-	°C	-	80
Drying time dry air dryer	-	h	-	4-6
Residual moisture content	ISO 15512	%	-	<0,2
Melt Temperature, for processing	-	°C	-	260-290
Screw Design	-	-	-	universal
Mould Temperature, injection moulding	-	°C	-	80
Moulding shrinkage (parallel)	ISO 294-4	%	2 mm	0,5
Moulding shrinkage (normal)	ISO 294-4	%	2mm	1,1

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.